

WEST

☐ Generate Collection

JP 7-18226

L4: Entry 47 of 64

File: DWPI

Jan 20, 1995

DERWENT-ACC-NO: 1995-094037
DERWENT-WEEK: 199513
COPYRIGHT 2002 DERWENT INFORMATION LTD

TITLE: Electric wire binding tape with good heat resistance, etc. - comprising base material, with pressure sensitive adhesive layer, comprising polyolefin with inorganic fire retardant, etc.

PATENT-ASSIGNEE:

ASSIGNEE

CODE

TOYO CHEM CORP

TOXP

PRIORITY-DATA: 1993JP-0187082 (June 30, 1993)

PATENT-FAMILY:

PUB-NO

PUB-DATE

LANGUAGE

PAGES

MAIN-IPC

JP 07018226 A

January 20, 1995

004

C09J007/02

APPLICATION-DATA:

PUB-NO

APPL-DATE

APPL-NO

DESCRIPTOR

JP 07018226A

June 30, 1993

1993JP-0187082

INT-CL (IPC): C09J 7/02

ABSTRACTED-PUB-NO: JP07018226A

BASIC-ABSTRACT:

Tape consists of a base material (A) and a pressure sensitive adhesive (B) layer formed on one surface of mfr. comprises: (1) uniformly dispersing 8-150 pts. wt. of inorganic fire retardant (C) in 100 pts. wt. of polyolefin resin (D) by kneading; (2) moulding the cpd. into films; (3) stretching the obtd. films by 1.5-6 times in the MD direction to adjust the film thickness to 0.03-0.5 mm; then (4) cutting the stretched films to tapes.

(D) includes polyethylenes, ethylene copolymers (rubbers), polypropylenes, propylene copolymers and butene copolymers.

The polyolefin cpd. for moulding (A) may contain particular and/or fibrous filler, pigment, plasticiser, lubricant, surfactant, and other conventional additives in addn. to (C) and (D) so far as electrical and/or mechanical performance does not deteriorate.

USE/ADVANTAGE - The process is suitable for mfg. electric wire binding tapes having good hand tear properties improved by adjusting the yield strength near to the tensile strength. The electric wire binding tapes obtd. has good heat resistance, fire retardancy, flexibility, mechanical properties and insulating property. They generate no toxic gases even in burning and so have good (C) may be selected from conventional inorganic fire retardants.

CHOSEN-DRAWING: Dwg.0/0

TITLE-TE RMS: ELECTRIC WIRE BIND TAPE HEAT RESISTANCE COMPRISE BASE MATERIAL PRESSURE SENSITIVE ADHESIVE LAYER COMPRISE POLYOLEFIN INORGANIC FIRE RETARD

DERWENT-CLASS: A17 A85 G03 X12

BEST AVAILABLE COPY

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開平7-18226

(43) 公開日 平成7年(1995)1月20日

(51) Int.Cl.⁴

C 0 9 J 7/02

識別記号

J H U

J J N

庁内整理番号

F I

技術表示箇所

審査請求 未請求 請求項の数1 F D (全 4 頁)

(21) 出願番号 特願平5-187082

(22) 出願日 平成5年(1993)6月30日

(71) 出願人 000222532

東洋化学株式会社

神奈川県鎌倉市台2丁目13番1号

(72) 発明者 庭山 喜司雄

神奈川県鎌倉市台2丁目13番1号 東洋化学株式会社内

(72) 発明者 沼上 登

神奈川県鎌倉市台2丁目13番1号 東洋化学株式会社内

(72) 発明者 内田 弘之

神奈川県鎌倉市台2丁目13番1号 東洋化学株式会社内

(54) 【発明の名称】 電線結束用テープの製造方法

(57) 【要約】

【目的】 電線結束用テープの降伏値と破断強度を近づけさせることにより手切れ性の向上を図った電線結束用テープの製造方法を提供する。また、電線結束用テープの製造方法は、従来から要求される高度の耐熱性、難燃性、燃焼しても有毒ガスの発生がない安全性、可撓性、機械的特性、さらに電気絶縁性を有する電線結束用テープの製造方法を提供する。

【構成】 基材を構成する樹脂としてのポリオレフィン系樹脂100重量部に対し無機難燃剤8～250重量部を配合し、その後、混練し均一に分散させてフィルム状に成形する。成形されたフィルム状のものを、そのフィルムのMD方向に1.5～6倍の延伸を行う一方、フィルムの厚を0.03～0.5mmに形成する。さらにこのフィルム状のものをテープ状に成形する。

【特許請求の範囲】

【請求項1】基材表面に粘着物質層を設けた電線結束用テープの製造方法であって、該基材を構成する樹脂としてのポリオレフィン系樹脂100重量部に対し無機難燃剤8〜250重量部を配合して混練し均一に分散させ、フィルム状に成形した後、該フィルムのMD方向に1.5〜6倍の延伸を行う一方、フィルム厚を0.03〜0.5mmに形成し、さらにテープ状に成形したことを特徴とする電線結束用テープの製造方法。

【発明の詳細な説明】

【0001】

【産業上の利用分野】本発明は、電気機器や自動車などの電線に電気絶縁材として使用される電線結束用テープに係り、特に、ポリオレフィン系樹脂組成物の基材表面に粘着物質層を設けた電線結束用テープであって、高度の柔軟性、一定な伸びを有すると共に従来と同様な燃焼しても有毒ガスを生じさせない安全性、可視性、機械的特性、さらに電気絶縁性に優れた電線結束用テープに関する。

【0002】

【従来の技術】従来、熱可塑性樹脂を基材とした電線結束用テープとしては、その組成物として熱可塑性樹脂100重量部に対し無機難燃剤（金属水和物など）100〜250重量部を添加したものが知られている（特開平4-363376号公報、特開平5-47249号公報）。

【0003】このような電線結束用テープにあつては、電線結束の際に作業者の手で巻きつけられた後、その手で切断される手切れ性が要求される。この手切れ性にあつては、テープが余りに伸びなくても伸び過ぎてもテープを手で切ることができないため、テープの特性として100〜400%の伸びを有するものが好ましい。また、電線を結束する際に任意な形状に巻きつけるため、柔軟性をも必要とされている。この柔軟性は、テープの基材の柔軟度で異なるが、一般にテープ厚で決定される。

【0004】この手切れ性や柔軟性に対し、有機ケイ素化合物を含有させたり、種々の基を有する樹脂を配合させたりしている（特開平4-363376号公報、特開平5-47249号公報）。

【0005】しかしながら、これら配合による処理によつては、ポリオレフィン系樹脂などに特有の降伏値（JIS K6760）と破断強度（JIS K6760）のズレが生じてしまうという課題がある。この課題は、電線結束作業を必要以上に手間取らせるという課題を引き起こした。これは、テープを手で切断する際、該テープが降伏点にまで伸びた後切断時まで再度伸びてしまうことから容易に切断できなかったためである。

【0006】

【発明が解決しようとする課題】したがって、本発明者

らは、このような課題を解決すべく鋭意研究を重ねた結果、電線結束用テープを製造する際、予めMD方向（テープ長手方向）に延伸させることにより、上記課題を解決できることを見だし、本発明を完成させた。

【0007】本発明の目的は、上記課題を解消すべく発明されたものであつて、電線結束用テープの降伏値と破断強度を近づけさせることにより手切れ性の向上を図る一方、従来から要求される高度の耐熱性、難燃性、燃焼しても有毒ガスを生じさせない安全性、可視性、機械的特性さらに電気絶縁性を有する電線結束用テープの製造方法を提供するものである。

【0008】

【課題を解決する手段】すなわち、本発明は、基材表面に粘着物質層を設けた電線結束用テープの製造方法であつて、該基材を構成する樹脂としてのポリオレフィン系樹脂100重量部に対し無機難燃剤8〜250重量部を配合して混練し均一に分散させ、フィルム状に成形した後、該フィルムのMD方向に1.5〜6倍の延伸を行う一方、フィルム厚を0.03〜0.5mmに形成し、さらにテープ状に成形したことを特徴とする電線結束用テープの製造方法である。

【0009】ここで、本発明においてポリオレフィン系樹脂100重量部に対し無機難燃剤8〜250重量部を配合したのは、無機難燃剤を余りに多く配合すると電線結束用テープ自身の機械的特性が劣化してしまい余りに少なく配合すると難燃効果を発揮させることができないためである。

【0010】MD方向に1.5〜6倍の延伸を行うのは、電線結束用テープのMD方向への伸びを調整するためと、テープ自体の降伏値と破断強度を近づけるためである。ここで、1.5〜6倍の範囲内に限定されているのは、伸びを100〜400%の範囲内に限定するためと、未延伸の状態からテープ自体の降伏値と破断強度を近づけるためであり、この条件内であればテープの手切れ性を維持できるためである。

【0011】フィルム厚を0.03〜0.5mmに限定したのは、樹脂の特性に影響をうけるが、この範囲内であれば、電線結束用テープとしての柔軟性を維持できるためである。

【0012】上記無機難燃剤としては、難燃効果を発揮し得るものであれば適宜選択できるものであり、例えば、水酸化アルミニウム、水酸化マグネシウム、水酸化カルシウム、水酸化バリウム、硼砂などの無機金属化合物の水和物、酸化スズの水和物、赤リン、酸化マグネシウム、酸化モリブデン、酸化ジルコニウム、酸化スズ、酸化アンチモン、ホウ酸亜鉛、メタホウ酸亜鉛、メタホウ酸バリウム、炭酸亜鉛、炭酸カルシウム、炭酸マグネシウム-カルシウム、炭酸バリウム、塩基性炭酸マグネシウム、ドロマイト、ハイドロタルサイトなどがあり、これらを2種以上併用することもできる。

【0013】ポリオレフィン系樹脂としては、高密度ポリエチレン、中密度ポリエチレン、超低密度ポリエチレン、高圧法低密度ポリエチレン、直鎖状低密度ポリエチレン、エチレン-プロピレン共重合体ゴム、エチレン-プロピレン-ジエン共重合体ゴム、エチレン-ブテン-1共重合体ゴムなどのオレフィン系ゴム、エチレン-酢酸ビニル共重合体などのエチレン-ビニルエステル共重合体、エチレン-エチルアクリレート共重合体、エチレン-(メタ)アクリル酸アルキルエステル共重合体などのエチレン- α 、 β -カルボン酸またはその誘導体との共重合体などのエチレン系(共)重合体、ポリプロピレン、プロピレン-エチレン共重合体などのポリプロピレン系共重合体、ポリブテン系重合体などがある。

【0014】また、本発明の電線結束用テープには、発揮させる難燃性や電気絶縁性などの機能を低下させない範囲で無機充填剤を併用することもでき、例えば、炭酸カルシウム、炭酸マグネシウム、硫酸カルシウム、硫酸カルシウム、酸化鉄、金属粉、アルミナ、三酸化アンチモン、グラファイト、炭化珪素、窒化珪素、窒化ホウ素、窒化アルミニウム、シリカ、カーボンブラック、クレー、珪藻土、タルク、珪砂、ガラス粉などの粉粒状充填剤、雲母、ガラス板、セリサイト、パイロフィライト、アルミフレークなどの金属箔、黒鉛などの平板状もしくは鱗片状充填剤、シラスバルーン、軽石などの中空状充填剤、ガラス繊維、グラファイト繊維、炭素繊維、アスベスト、ウオラストナイトなどの鉱物繊維などがある。

*【0015】なお、上記電線結束用テープには、発揮させる耐熱性、難燃性や電気絶縁性などの機能を低下させない範囲で架橋促進剤、可塑剤、滑剤、界面活性剤、加工助剤、顔料等が併用されるのは勿論のことである。また、本発明のテープ基材の製造にあつては各添加剤を単軸または二軸混合機、パンバリーミキサー、ニーダー、オープンロールミキサーなどで混合し、熔融押出法やカレンダーロール成形法によってフィルム状に成形するものである。

10 【0016】

【作用】本発明によれば、基材表面に粘着物質層を設けた電線結束用テープの製造方法であつて、該基材を構成する樹脂としてのポリオレフィン系樹脂100重量部に対し無機難燃剤8~250重量部を配合して混練し均一に分散させ、フィルム状に成形した後、該フィルムのMD方向に1.5~6倍の延伸を行う一方、フィルム厚を0.03~0.5mmに形成し、さらにテープ状に成形したことを特徴とし、これにより、電線結束用テープの降伏値と破断強度を近づけさせることにより手切れ性を向上させることができる。

【0017】

【実施例】本発明にかかる実施例を、詳細に説明し、この実施例によって製造された電線結束用テープの特性を表1に開示する。

【0018】

【表1】

延伸倍率 /MD方向	第1実施例			第2実施例		
	降伏値 kgf/cm ²	伸び %	破断強度 kgf/cm ²	降伏値 kgf/cm ²	伸び %	破断強度 kgf/cm ²
未延伸	65	650	115	70	600	120
1.5	80	400	120	85	400	125
2.5	95	350	135	110	320	135
3.5	110	280	145	130	250	145
4.5	135	220	150	140	200	150
5.5	150	150	160	160	120	160
6.5	170	95	170	170	90	170

【0019】第1実施例にかかる電線結束用テープは、※50※ポリオレフィン系樹脂としてのE EA (エチレン-エチ

ル-アクリレート共重合体) 100重量部と、赤リン10重量部と、炭酸カルシウム60重量部とを主成分としたポリオレフィン系樹脂組成物をバンバリーミキサーで混練し、均一に分散させる。その後、このポリオレフィン系樹脂組成物を170℃に設定したダイによりフィルム状に押出成形し、100℃の状態を表1に示すそれぞれの倍率でMD方向に延伸してフィルム厚を130 μ mとし、その一方の面に粘着剤を積層した後、最後にテープ状に切断した。

【0020】この第1実施例で製造された電線結束用テープは、表1に示すように、未延伸の状態(従来の状態)では伸びが650%であり、所望の400%以下にならなかった。6.5倍の延伸のときには、伸びが95%であり、所望の100%以上にならなかった。また、延伸倍率が1.5~5.5の場合には、伸びが100~400%の範囲内であり、未延伸の場合の降伏値と破断強度(両者共、JISK6760)との差が50kgf/cm² あったのが、40kgf/cm² 以下になり、降伏値と破断強度との差が近似した。

【0021】また、第2実施例にかかる電線結束用テープについて説明する。第2実施例は、上記第1実施例と同様な製造方法により製造したものであり、ポリオレフ

イン系樹脂としてのEEA100重量部と水酸化マグネシウム100重量部とを主成分としたポリオレフィン系樹脂組成物を基材にした電線結束用テープであり、製造後のテープ厚を100 μ mとしたものである。

【0022】第2実施例にあっても、未延伸の状態(従来の状態)に比べ、伸びが100~400%の範囲内であり、降伏値と破断強度との差が近似したものであった。

【0023】

10 【発明の効果】本発明は、基材表面に粘着物質層を設けた電線結束用テープの製造方法であって、該基材を構成する樹脂としてのポリオレフィン系樹脂100重量部に対し無機難燃剤8~250重量部を配合して混練し均一に分散させ、フィルム状に成形した後、該フィルムのMD方向に1.5~6倍の延伸を行う一方、フィルム厚を0.03~0.5mmに形成し、さらにテープ状に成形したことを特徴とし、これにより、電線結束用テープの降伏値と破断強度を近づけさせることにより手切れ性の向上を図る一方、従来から要求される高度の耐熱性、難燃性、燃焼しても有毒ガスを生じさせない安全性、可撓性、機械的特性、さらに電気絶縁性を有するという効果を有する。

90006087-012302

* NOTICES *

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention] this invention relates to the tape for electrical-wire union used for electrical wire, such as an electrical machinery and apparatus and an automobile, as electric-insulation material, it is the tape for electrical-wire union which prepared the adhesion matter layer in the base-material front face of a polyolefine system resin constituent especially, and even if it burns, it relates to the same safety as the former which does not produce a poisonous gas, flexibility, a mechanical property, and the tape for electrical-wire union that is further excellent in an electric insulation etc., while it has advanced flexibility and fixed elongation.

[0002]

[Description of the Prior Art] Conventionally, what added the inorganic flame retarders (metal hydrate etc.) 100 - 250 weight section to the thermoplastics 100 weight section as the constituent as a tape for electrical-wire union which made thermoplastics the base material is known (JP,4-363376,A, JP,5-47249,A).

[0003] If it was in such a tape for electrical-wire union, after twisting by an operator's hand in the case of electrical-wire union, the solatium nature cut by the hand is demanded. Since a tape cannot be cut by hand even if a tape is not extended to remainder and it is extended too much, if it is in this solatium nature, what has 100 - 400% of elongation as a property of a tape is desirable. Moreover, flexibility is also needed, in order to twist around arbitrary configurations, in case electrical wire is banded together. Although these flexibility differs with the degree of adaptability of the base material of a tape, generally it is determined by tape

[0004] To this solatium nature and flexibility, an organic silicon compound is made to contain or the resin which has the various bases is combined (JP,4-363376,A, JP,5-47249,A).

[0005] However, by processing by these combination, the technical problem that gap of a yield value (JIS K6760) peculiar to a polyolefine system resin etc. and breaking strength (JIS K6760) will arise occurs. This technical problem caused the technical problem that electrical-wire union work was delayed beyond the need. This is because it has not cut from being again extended till a disconnection easily, after extending this tape even to the yield point, in case a tape is cut by hand.

[0006]

[Problem(s) to be Solved by the Invention] Therefore, as a result of repeating a research zealously that such a technical problem should be solved, in case this invention persons manufactured the tape for electrical-wire union, by making it extend in the orientation (tape longitudinal direction) of MD beforehand, they found out that the above-mentioned technical problem was solvable, and completed this invention.

[0007] The purpose of this invention is invented that the above-mentioned technical problem should be canceled, and while it aims at enhancement in solatium nature by making the yield value and breaking strength of the tape for electrical-wire union brought close, even if it burns, it offers the advanced thermal resistance demanded from the former, fire retardancy, the safety which does not produce a poisonous gas, flexibility, and the manufacture technique of the tape for electrical-wire union of having an electric insulation in a mechanical property pan.

[0008]

[Means for Solving the Problem] Namely, this invention is the manufacture technique of the tape for electrical-wire union of having prepared the adhesion matter layer in the base-material front face. Blend and knead the inorganic flame retarder 8 - 250 weight section to the polyolefine system resin 100 weight section as a resin which constitutes this base material, and it is made to distribute uniformly. After fabricating in the shape of a film, while performing 1.5 to 6 times as many extension as this in the orientation of MD of this film, it is the manufacture technique of the tape for electrical-wire union characterized by having formed film ** in 0.03-0.5mm, and fabricating in the shape of a tape further.

[0009] Here, in this invention, the inorganic flame retarder 8 - 250 weight section were blended to the polyolefine system resin 100 weight section for the ability not to exhibit [if many inorganic flame retarders to remainder are blended, the mechanical property of a tape own / for electrical-wire union / will deteriorate, and / if it blends with remainder few] a fire-resistant effect.

[0010] 1.5 to 6 times as many extension as this is performed in the orientation of MD for bringing the yield value and breaking strength of the tape [itself] close, in order to adjust the elongation to the orientation of MD of the tape for electrical-wire union. Here, in order to limit elongation to 100 - 400% of within the limits, if it is for bringing the yield value and breaking strength of the tape [itself] close from the status that it does not extend and it is in this condition, it will be limited within the limits of 1.5 to

6 times for the solatium nature of a tape being maintainable.

[0011] Although influence is received in the property of a resin, film ** was limited to 0.03-0.5mm for the flexibility as a tape for electrical-wire union being maintainable, when it was this within the limits.

[0012] It is what can be suitably chosen as the above-mentioned inorganic flame retarder if a fire-resistant effect can be demonstrated. For example, an aluminum hydroxide, a magnesium hydroxide, a calcium hydroxide, The hydrate of inorganic metallic compounds, such as a barium hydroxide and a borax, the hydrate of the tin oxide, Red phosphorus, a magnesium oxide, a molybdenum oxide, a zirconium oxide, the tin oxide, There are an antimony oxide, boric-acid zinc, metaboric acid zinc, metaboric acid barium, a zinc carbonate, a calcium carbonate, magnesium-carbonate-calcium, a barium carbonate, a basic magnesium carbonate, a dolomite, a hydrotalcite, etc., and two or more sorts of these can also be used together.

[0013] As a polyolefine system resin, a high density polyethylene, a medium density polyethylene, A super-low density polyethylene, a high-pressure-process low density polyethylene, a straight chain-like low density polyethylene, Ethylene-propylene copolymer rubber, ethylene-propylene-diene copolymer rubber, Ethylene-vinyl-ester copolymers, such as olefin system rubber, such as ethylene-butene-1 copolymer rubber, and an ethylene-vinyl acetate copolymer, Ethylene, such as an ethylene-ethyl acrylate copolymer and an ethylene-(meta) acrylic-acid alkyl ester copolymer - Ethylene system (**) polymers, such as alpha and beta-carboxylic acid or a copolymer with the derivative, There are polypropylene system copolymers, such as a polypropylene and propylene-ethylene copolymer, a polybutene system polymer, etc.

[0014] Moreover, an inorganic bulking agent can also be used together in the domain which does not reduce the functions to exhibit, such as fire retardancy and an electric insulation, on the tape for electrical-wire union of this invention. For example, a calcium carbonate, a magnesium carbonate, a calcium sulfate, a calcium silicate, An iron oxide, a metal powder, an alumina, an antimony trioxide, graphite, a silicon carbide, A silicon nitride, boron nitride, an aluminium nitride, a silica, carbon black, Powder granular bulking agents, such as clay, diatomaceous earth, talc, silica sand, and a glass powder, a mica, There are mineral fibers, such as hollow-like bulking agents, such as plate-like [, such as metallic foils, such as a glass plate, a sericite, a pyrophyllite, and aluminum flakes and a graphite,] or a scale-like bulking agent, a milt balloon, and a pumice, a glass fiber, a graphite fiber, a carbon fiber, asbestos, and a wollastonite, etc.

[0015] in addition, the domain which does not reduce functions, such as the thermal resistance and the fire retardancy to exhibit, and an electric insulation, on the above-mentioned tape for electrical-wire union -- bridge formation -- it comes out not to mention an accelerator, a plasticizer, a lubricant, a surfactant, processing aid, a pigment, etc. being used together Moreover, if it is in a manufacture of the tape base material of this invention, each additive is mixed by a monopodium or the 2 shaft mixer, the Banbury mixer, the kneader, the oven roll mixer, etc., and it fabricates in the shape of a film by the melting extrusion method or the calendaring-roll fabricating method.

[0016]

[Function] According to this invention, it is the manufacture technique of the tape for electrical-wire union of having prepared the adhesion matter layer in the base-material front face. Blend and knead the inorganic flame retarder 8 - 250 weight section to the polyolefine system resin 100 weight section as a resin which constitutes this base material, and it is made to distribute uniformly.

After fabricating in the shape of a film, while performing 1.5 to 6 times as many extension as this in the orientation of MD of this film, film ** is formed in 0.03-0.5mm, and it is characterized by fabricating in the shape of a tape further. by this Solatium nature can be raised by making the yield value and breaking strength of the tape for electrical-wire union brought close.

[0017]

[Example] Such an example is explained to this invention in detail, and the property of the tape for electrical-wire union manufactured according to this example is indicated to Table 1.

[0018]

[Table 1]

延伸倍率 /MD方向	第1実施例			第2実施例		
	降伏値 kgf/cm ²	伸び %	破断強度 kgf/cm ²	降伏値 kgf/cm ²	伸び %	破断強度 kgf/cm ²
未延伸	65	650	115	70	600	120
1.5	80	400	120	85	400	125
2.5	95	350	135	110	320	135
3.5	110	280	145	130	250	145
4.5	135	220	150	140	200	150
5.5	150	150	160	160	120	160
6.5	170	95	170	170	90	170

[0019] Such a tape for electrical-wire union kneads the polyolefine system resin constituent which made the principal component EEA(ethylene-ethyl acrylate copolymer) 100 weight section as a polyolefine system resin, the red phosphorus 10 weight section, and the calcium-carbonate 60 weight section by the Banbury mixer at the 1st example, and it is made to distribute uniformly. Then, after having carried out extrusion molding to the shape of a film with the die which set this polyolefine system resin constituent as 170 degrees C, having extended in the orientation of MD for each scale factor shown in Table 1 in the 100-degree C status, having set film ** to 130 micrometers and carrying out the laminating of the binder to the field of one of these, it cut in the shape of a tape at the last.

[0020] In the state of un-extending (the conventional status), elongation is 650% and the tape for electrical-wire union manufactured in this 1st example did not become 400% or less of a request, as shown in Table 1. At the time of 6.5 times as many extension as this, elongation is 95% and did not become 100% or more of a request. Moreover, the difference of the yield value in the case of elongation being 100 - 400% of within the limits, and having not extended, when draw magnifications are 1.5-5.5, and breaking strength (both JISK6760) is 50kgf/cm². It is 40kgf/cm² that it was. It became below and the difference of a yield value and breaking strength approximated.

[0021] Moreover, such a tape for electrical-wire union is explained to the 2nd example. The 2nd example is manufactured by the same manufacture technique as the 1st above-mentioned example, is the tape for electrical-wire union which made the base material the polyolefine system resin constituent which made the principal component EEA 100 weight section as a polyolefine system resin, and the magnesium-hydroxide 100 weight section, and sets tape ** after a manufacture to 100 micrometers.

[0022] Even if it was in the 2nd example, compared with the status (the conventional status) that it does not extend, elongation is 100 - 400% of within the limits, and the difference of a yield value and breaking strength approximated.

[0023]

[Effect of the Invention] this invention is the manufacture technique of the tape for electrical-wire union of having prepared the adhesion matter layer in the base-material front face. Blend and knead the inorganic flame retarder 8 - 250 weight section to the polyolefine system resin 100 weight section as a resin which constitutes this base material, and it is made to distribute uniformly. After fabricating in the shape of a film, while performing 1.5 to 6 times as many extension as this in the orientation of MD of this film, film ** is formed in 0.03-0.5mm, and it is characterized by fabricating in the shape of a tape further. by this While aiming at enhancement in solatium nature by making the yield value and breaking strength of the tape for electrical-wire union brought close, even if it burns, it has the advanced thermal resistance demanded from the former, fire retardancy, the safety which does not produce a poisonous gas, flexibility, a mechanical property, and the effect of having an electric insulation further.

[Translation done.]

* NOTICES *

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] It is the manufacture technique of the tape for electrical-wire union of having prepared the adhesion matter layer in the base-material front face. Blend and knead the inorganic flame retarder 8 - 250 weight section to the polyolefine system resin 100 weight section as a resin which constitutes this base material, and it is made to distribute uniformly. The manufacture technique of the tape for electrical-wire union characterized by having formed film ** in 0.03-0.5mm, and fabricating in the shape of a tape further while performing 1.5 to 6 times as many extension as this in the orientation of MD of this film, after fabricating in the shape of a film.

[Translation done.]

200210-28090006